




MIPAN® glurex® melts at much lower temperatures than other conventional fibers, which allows it to provide an adhesive bond to the fibers.

[Characteristics]


- Elastic bands for strengthening picot
- Edge-bonding of raschel lace etc.
- Bonded sewing thread
- Chenille yarn for covers of furniture and automobile seat

[Specifications]

ITEM	DENIER	FILA	TEMP.	SETTING CONDITION
G85	20	3	85~100℃	90~100℃/40min before dyeing
	30	5		
	50	10		
	70	10		
G125	20	3	110~120℃	110~120℃/40~60min before dyeing
	50	10		
	70	10		
G140	20	3	130~140℃	



With glurex®



Without glurex®

[In-bonded sewing thread]

